

T E S T C E R T I F I C A T E

ST-23-07-06-01

Product: Laminat Flooring "8 mm - derzli / with bevel"

Producer: AGT Agac Sanayi ve Tic. A.S.
Organize Sanayi Bölgesi
S.Kisim, 35. Cadde
07190 DÖSEMEALTI, ANTALYA
TÜRKIYE

Order: Determination of Laminate Flooring Topical Moisture Resistance
according to ISO 4760:2022-05

Test report: 2723297


Test results:

Property	Result	Evaluation according to prEN 13329:2023, table 3
Water resistance according to ISO 4760:2022-5	Qualitative recovery swell rating (final average): 2 Recovery swell (final average): 0,19 mm	Additional requirements according to table 3 are fulfilled
Resistance of mechanical joints to water leakage according to ISO 4760:2022-05 annex D	No water leak through the joints after 24 h water exposure	Additional requirements according to table 3 are fulfilled

Dresden, 06/07/2023



Head of laboratory

Engineer in charge